# NHÀ PHÂN PHỐI ỦY QUYỀN: CÔNG TY VINDEC

# Technical Data Sheet



## FEROLITE NAM 33 NON ASBESTOS GASKET JOINTING SHEET

AM 33 Ferolite NAM.

Itte NAM 33 Ferolite NAM.

Itte NAM 33 Ferolite NAM.

AM 33 Ferolite NAM.

AM 33 Ferolite NAM.

AM 33 Ferolite NAM.

### Applications:

Gasket material with controlled swell properties in oil, wide range of application in automotive and chemical industry. Suitable to seal off hydraulic, engines, transmission and refrigerating oils as well as other hydrocarbons. Also applicable for joints with low sealing pressure like housing, valve covers, oil pans etc.

### General data:

Material Composition
Aramid Fibre, Mineral Fiber
(Type of fibres)

Binders

**OPERATING CONDITION** 

Max.Peak Temp400°CMax. Continuous Temp270°CMax.Continuous Temp.with steam240°C

Max. Operating Pressure 150 Kg/cm<sup>2</sup>

# FEROLITE NAM 33 PR 120S 120

### Physical Properties:

The following Information applies to material thickness 2.0 mm.

S.NO.	PROERTIES	TEST METHOD	UNIT	SPECIFIED VALUE
1.	DENSITY		gm/cm <sup>3</sup>	1.70 - 2.00
2.	TENSILE STRENGTH			
	(a) ACC to ASTM F152(ACROSS GRAIN)		N/mm²	> 12
	(b) ACC to DIN52910 (ACROSS GRAIN)		N/mm²	> 9
3.	COMPRESSIBILITY	ASTM F36A	%	5 – 15
4.	RECOVERY	ASTM F36A	%	> 50
5.	FLUID ABSORPTION	ASTM F 146		
	(a) IN ASTM OIL NO. 3			
	INCREASE IN MASS		%	8-30
	INCREASE IN THICKNESS		%	8-30
	(b) IN FUEL B	ASTM F 146		
	INCREASE IN MASS		%	8-30
	INCREASE IN THICKNESS		%	8-30
	(c) IN WATER/ANTIFREEZE	ASTM F 146		
	INCREASE IN MASS		%	15
	INCREASE IN THICKNESS		%	7
6.	IGNITION LOSS	DIN 52911	%	< 35
7.	SEALABILITY AGAINST Nitrogen	DIN 3535	cm³/min.	< 1.0
8.	STRESS RESISTANCE			
	16h 300°C	DIN 52913	N/mm²	~ 20
	16h 175°C	DIN 52913	N/mm²	~ 30