

# Industrial Coatings

## Technical Data Sheet

# Irganox<sup>®</sup> 1010



### Product Description


Irganox<sup>®</sup> 1010 is a highly effective, non-discoloring, sterically hindered primary phenolic antioxidant stabilizer that protects organic substrates against thermo-oxidative degradation.

### Key Features & Benefits

- Good compatibility
- High resistance to extraction
- Low volatility
- Odorless
- Can be used in combination with other additives
- Manufactured using a tin-free process

### Chemical Composition

Pentaerythritol tetrakis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate)



## Properties

### Typical Properties

Appearance	white, free-flowing powder
CAS number	6683-19-8
Molecular weight	1,178 g/mol
Melting range	110 – 125°C
Flash point	297°C
Vapor pressure at 20°C	7 E-10 Pa (extrapolated)
Density at 20°C	1.15 g/ml
Density (bulk)	530 – 630 g/l

### Solubility at 20°C (g/100 g solution)

Acetone	47
Chloroform	71
Ethanol	1.5
Ethyl acetate	47
n-Hexane	0.3
Methanol	0.9
Methylene chloride	63

These typical values should not be interpreted as specifications.

## Applications

Irganox® 1010 is used in polyolefins such as polyethylene, polypropylene, polybutene, as well as, in olefin co-polymers such as ethylene vinyl acetate co-polymers. It is also recommended for the processing of polymers such as polyacetals, polyamides, and polyurethanes, polyesters, PVC, styrene homo- and co-polymers, ABS, elastomers such as butyl rubber (IIR), SBS, SEBS, EPM, and EPDM, other synthetic rubbers, adhesives, natural and synthetic tackifiers resins, and other organic substrates.

It has good compatibility, high resistance to extraction, low volatility, and odorless. Irganox® 1010 can be used in combination with other additives such as co-stabilizers (thioethers, phosphites, phosphonites), light stabilizers, and other functional stabilizers.

Irganox® 1010 is recommended for applications such as:

- Solvent-based coating applications
- Tackifier resins
- Hot-melt adhesives

### **Recommended Concentrations**

The amount of Irganox® 1010 required for optimum performance should be determined in trials covering a concentration range. Concentrations up to several percent may be used depending on the substrate, processing conditions, requirements of the end application, and long term thermal stability requirements.

0.05 – 0.1% ppm of Irganox® 1010 provides long term thermal stability to the polymer.

<u>Application</u>	<u>Concentration</u>
Polyolefins	0.05 – 0.4%
Hot melt adhesives	0.2 – 1%
Synthetic tackifier resins	0.1 – 0.5%
Solvent-based coatings	0.2 – 1.0%

---

## Safety

### **General**

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State, and Local health and safety regulations, thorough ventilation of the workplace, good skin care, and wearing of protective goggles.

### **Material Safety Data Sheet**

All safety information is provided in the Material Safety Data Sheet for Irganox® 1010.

---

## Storage

Properly stored and protected, an unopened container of Irganox® 1010 should have a shelf life of at least one year.

---

## Important

The descriptions, designs, and data contained herein are presented for your guidance only. Because there are many factors under your control which may affect processing or application/use it is necessary for you to make appropriate tests to determine whether the product is suitable for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, OR DATA MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, DATA OR DESIGNS PROVIDED BE PRESUMED TO BE A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, and data furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for same or results obtained from use thereof, all such being given to you and accepted by you at your risk.

*Irganox is a registered trademark of BASF Group.*

BASF Corporation, 2015



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.  
For more information on Responsible Care® go to:  
U.S.: [www.basf.us/responsiblecare\\_usa](http://www.basf.us/responsiblecare_usa)  
Canada: [www.basf.us/responsiblecare\\_canada](http://www.basf.us/responsiblecare_canada)  
México: [www.basf.us/responsiblecare\\_mexico](http://www.basf.us/responsiblecare_mexico)

BASF Corporation  
Dispersions and Pigments  
11501 Steele Creek Road  
Charlotte, North Carolina 28273  
Phone: (800) 251 – 0612  
Email: [edtech\\_info@basf.com](mailto:edtech_info@basf.com)  
[www.basf.us/dpsolutions](http://www.basf.us/dpsolutions)