

B1A

Technical Data Sheet

DESCRIPTION

B1A is a maleic anhydride modified polypropylene with high grafting rate.

TYPICAL PHYSICAL & CHEMICAL PROPERTIES

Characteristics	Value	Unit	Test Method
Appearance	Granules		
Color	White or light yellow		
Density	0.92	g/cm ³	ASTM D792
Melt Flow Rate (190°C/2.16kg)	70-110	g/10min	ASTM D1238
Maleic Anhydride Content	High	wt%	Maker's Method ^[1]

Notes ^[1] LOW<0.4wt%; Middle(0.4wt%-0.8wt%); High>0.8wt%.

APPLICATIONS

To be used as coupling agent in polypropylene base compounds to strengthen the adhesion between infill materials and polymer matrix.

To be used as compatibilizers to improve the compatibility between polyamide and polypropylene.

STORAGE, HANDLING & SAFETY

B1A should be stored in dry conditions and protected from UV-light. Improper storage conditions may cause degradation and have consequences on physical properties of the product.

SHELF LIFE

1 years from the date of delivery, in unopened packaging.

This fact sheet is intended as general advice.

Disclaimer: The information submitted in this publication is based on current knowledge and experience. In view of the many factors that may affect its application, this data does not relieve the user from carrying out their own tests. The data does not imply assurance of certain properties or of suitability for a specific purpose. It is the responsibility of the user to ensure that any proprietary rights and existing laws and legislation are observed.